



Northern Forest Products

Species Weights
Kiln Dried Weight per Board Foot



| Species | Rough | H/M | 13/16" |
|--------------------|-------|-----|--------|
| Alder | 2.3 | 2.2 | 1.9 |
| Ash | 3.4 | 3.2 | 2.8 |
| Aspen | 2.2 | 2.1 | 1.8 |
| Basswood | 2.1 | 2.0 | 1.7 |
| Domestic Beech | 3.6 | 3.4 | 2.9 |
| Paper White Birch | 3.1 | 2.9 | 2.5 |
| Yellow Birch | 3.5 | 3.3 | 2.9 |
| Butternut | 2.2 | 2.1 | 1.8 |
| Aromatic Red Cedar | 2.6 | 2.5 | 2.1 |
| Cherry | 2.9 | 2.7 | 2.4 |
| Cypress | 2.6 | 2.4 | 2.1 |
| Hickory | 4.1 | 3.9 | 3.4 |
| Hard Maple | 3.5 | 3.3 | 2.9 |
| Soft Maple | 3.0 | 2.8 | 2.5 |
| Red Oak | 3.6 | 3.4 | 2.9 |
| White Oak | 3.8 | 3.6 | 3.1 |
| Pine, White | 2.1 | 2.0 | 1.7 |
| Poplar | 2.5 | 2.3 | 2.0 |
| Walnut | 3.2 | 3.0 | 2.6 |
| Anigre | 4.3 | 4.0 | 3.5 |
| European Beech | 3.8 | 3.5 | 3.0 |
| Bubinga | 4.4 | 4.1 | 3.6 |
| Jatoba | 4.7 | 4.4 | 3.8 |
| Lyptus | 4.4 | 4.1 | 3.6 |
| African Mahogany | 2.5 | 2.3 | 2.0 |
| Honduras Mahogany | 2.7 | 2.5 | 2.2 |
| Makore | 3.3 | 3.0 | 2.6 |
| Padouk | 4.4 | 4.1 | 3.6 |
| Purpleheart | 4.0 | 3.8 | 3.3 |
| Sapele | 3.4 | 3.2 | 2.8 |
| Teak | 3.2 | 3.0 | 2.6 |
| Zebrawood | 3.6 | 3.4 | 2.9 |



Northern Forest Products
2050 Main Street
Centerville, MN 55038
651-429-9990
651-429-9993 fax